

AMENDMENTS TO THE CLAIMS:

This listing of claims will replace all prior versions, and listings, of claims in the application:

LISTING OF CLAIMS:

1. (Currently Amended) A dissymmetric particle of nanometric or mesoscopic size, that has ~~an inorganic~~ a first part ~~comprised of a~~ consisting of an inorganic material A and ~~an organic~~ a second part ~~comprised of a~~ consisting of an organic material B, wherein:
 - the inorganic material A is a mineral oxide or a metal;
 - the organic material B is a polymer comprised of recurrent units derived from a vinyl compound;
 - the ~~organic~~ second part is [[a]] constituted by a single substantially spherical nodule having an outer surface which is bound by physicochemical or covalent interactions to an outer surface of the ~~inorganic~~ first part so as to form said dissymmetric particle; and
 - the size of each of the parts is between 5 nm and 1 μ m.
2. (Previously Presented) The particle as claimed in claim 1, wherein its size is between 1 nm and 100 nm or between 100 nm and 1 μ m.
3. (Previously Presented) The particle as claimed in claim 1, wherein the inorganic material A is an oxide chosen from silica, iron oxides, aluminosilicates, titanium dioxide or alumina.

4. (Previously Presented) The particle as claimed in claim 3, wherein the inorganic material A is a metal chosen from metals that are stable in an aqueous medium.
5. (Previously Presented) The particle as claimed in claim 1, wherein the inorganic material bears an organic group.
6. (Previously Presented) The particle as claimed in claim 5, wherein the organic group is chosen from alkyl groups, amine functions, thiol functions and nitrile functions.
7. (Previously Presented) The particle as claimed in claim 1, wherein the polymer comprises recurrent units $-CR=CR'-$, which may be identical or different, in which:
 - R represents H or an alkyl group;
 - R' represents H, an alkyl group, an aryl group, an alkylaryl group, an alkenylaryl group, a pyridyl group, a nitrile group, a group $-COOR''$ or a group $-OC(O)R''$ in which R'' is H, an alkyl or an alkenyl.
8. (Previously Presented) The particle as claimed in claim 7, wherein the alkyl group or the aryl group bears a functional group.
9. (Previously Presented) The particle as claimed in claim 7, wherein the

polymer is crosslinked or noncrosslinked.

10. (Previously Presented) The particle as claimed in claim 1, wherein the inorganic part has the shape of a sphere.
11. (Currently Amended) The particle as claimed in claim 10, wherein ~~it~~ the particle has the shape of a dumbbell, the organic and inorganic parts having substantially the same size.
12. (Currently Amended) The particle as claimed in claim 10, wherein ~~it~~ the particle has the shape of a snowman, the inorganic part having a size ~~that is~~ clearly different from the organic part.
13. (Previously Presented) The particle as claimed in claim 1, wherein the inorganic part has the shape of an ellipse, of a disk, of a block or of a rod.
14. (Previously Presented) The particle as claimed in claim 1, wherein the inorganic material is silica and the organic material B is a polystyrene or a copolymer of styrene and of divinylbenzene.
15. (Withdrawn) A method for preparing dissymmetric particles as claimed in claim 1, wherein it comprises the following steps:
 - a) during a first step, the surface of particles having a size of between 5 nm and 1 μ m and comprised of the inorganic material A is modified with a

coupling agent C comprising a function F_C which exhibits affinity for one or more precursors of the polymer B;

- b) during a second step, the modified inorganic particles obtained at the end of step a) are brought into contact with the precursor(s) of the polymer B, in the presence of a free-radical initiator and of a surfactant in solution in a solvent, in proportions that allow the formation of one nodule of polymer per inorganic particle.

16. (Withdrawn) The method as claimed in claim 15, wherein the particles are extracted from the reaction medium by evaporation of the solvent or by lyophilization.
17. (Withdrawn) The method as claimed in claim 15, wherein the initial inorganic particles are used, for step a), in the form of a colloidal suspension for which the solids content is between 2 and 35%, and for which the pH is adjusted so as to allow the interaction with the coupling agent C.
18. (Withdrawn) The method as claimed in claim 15, wherein the inorganic particles are silica particles having a diameter of approximately 100 nm.
19. (Withdrawn) The method as claimed in claim 15, wherein the function F_C is a vinyl group, or a vinyl, allyl, styryl, methacryloyl or acryloyl group.
20. (Withdrawn) The method as claimed in claim 15, wherein step a) is carried out

by bringing the inorganic particles into contact with a macromonomer consisting of a macromolecule having a hydrophilic chain that ends with a polymerizable function F_C , and the reaction medium is stirred.

21. (Withdrawn) The method as claimed in claim 20, wherein the macromonomer is chosen from poly(ethylene oxide)s, hydroxycelluloses, poly(vinylpyrrolidone)s, poly(acrylic acid)s or poly(polyvinyl alcohol)s, said compounds bearing the function F_C .
22. (Withdrawn) The method as claimed in claim 15, wherein step a) is carried out by covalent grafting of a coupling agent bearing a function F_C that is copolymerizable with the precursor(s) of the polymer B.
23. (Withdrawn) The method as claimed in claim 22, wherein the inorganic part A is a mineral oxide and the coupling agent is chosen from organosilanes corresponding to the formula $R^1_nSiX_{4-n}$ ($n = 1$ to 3), in which X is a hydrolyzable group and R^1 is a radical comprising the functional group F_C .
24. (Withdrawn) The method as claimed in claim 23, wherein the coupling agent is a methacryloylalkyltrialkoxysilane.

25. (Withdrawn) The method as claimed in claim 22, wherein the inorganic particle A is a metal, and the coupling agent is chosen from organothiols R^1SH or amines R^1NH_2 in which R^1 is a substituent bearing the functional group F_C .
26. (Withdrawn) The method as claimed in claim 25, wherein the coupling agent is 4-vinylaniline.
27. (Withdrawn) The method as claimed in claim 15, wherein step a) is carried out by suspending the inorganic particles at a pH close to neutrality, and adding an amphiphilic compound consisting of a hydrophobic part that has a polymerizable group and of a polar head that bears a charge opposite to that of the surface of the particles.
28. (Withdrawn) The method as claimed in claim 27, wherein the amphiphilic molecules are chosen from compounds derived from styrene sulfonates and quaternary alkylammoniums, the two types of compounds bearing a hydrophobic group.
29. (Withdrawn) The method as claimed in claim 15, wherein step b) is carried out by bringing the modified particles of inorganic material A obtained at the end of step a) into contact with a monomer which is a precursor of the polymer B, in the presence of a polymerization initiator, said monomer bearing functions F_B capable of reacting with the functions F_C .

30. (Withdrawn) The method as claimed in claim 15, wherein step b) is carried out by bringing the particles of material A obtained at the end of step a) into contact with an oligomer of the polymer B, in the presence of a polymerization initiator.
31. (Withdrawn) The method as claimed in claim 15, wherein the dissymmetric particles obtained at the end of step b) are subjected to a further treatment aimed at modifying the surface groups of the material A that were not modified during step b).
32. (Withdrawn) The method as claimed in claim 29, wherein the monomer precursor is chosen from compounds having a vinyl group that plays the role of polymerizable function F_B .
33. (Withdrawn) The method as claimed in claim 32, wherein the monomer corresponds to formula $HRC=CHR'$ in which:
- R represents H or an alkyl group;
 - R' represents H, an alkyl group, an aryl group, an alkylaryl group, an alkenylaryl group, a pyridyl group, a nitrile group, a group $-COOR''$ or a group $-OC(O)R''$ in which R'' is H, an alkyl or an alkenyl.
34. (Withdrawn-Currently Amended) The method as claimed in claim 33, wherein the monomer is chosen from styrene, α -methylstyrene, vinylpyridine, vinyl

acetate, vinyl propionate, methyl methacrylate, ethyl acrylate, butyl acrylate, ethylhexyl methacrylate, acrylonitrile and or methacrylonitrile.

35. (Withdrawn) The method as claimed in claim 29, wherein a mixture comprising one or more monomers having a group F_B , and a monomer comprising a second group F_B , is used.
36. (Withdrawn) The method as claimed in claim 30, wherein the oligomer is chosen from the polymers or copolymers obtained from monomers having a vinyl group that plays the role of polymerizable function F_B and optionally bearing a function that is crosslinking in nature.
37. (Withdrawn) The method as claimed in claim 15, wherein the solvent is chosen from water or water-alcohol mixtures in water/alcohol proportions of between 100/0 and 50/50.
38. (Withdrawn) The method as claimed in claim 15, wherein the surfactant is chosen from anionic, cationic or nonionic surfactants.
39. (Previously Presented) The particle of claim 1, wherein the size of each of the parts is between 50 nm and 250 nm.